

Amendments to the Claims:

This listing of claims will replace all prior versions in the application.

Listing of Claims:

1. (currently amended) Foamed cellular particles for use in forming foam articles and said foamed cellular particles being pre-expanded polymer particles that are formed from expandable polymer particles, said foamed cellular particles having a bulk density ranging between about 34.3 pounds per cubic foot (550 kilograms per cubic meter) and 12.5 pounds per cubic foot (200 kilograms per cubic meter) and ~~[[a]]~~ an organic blowing agent in an amount ranging between ~~[[2.0]]~~ 2.5 and 5.0 wt % based on the polymer, and for a predetermined time at room temperature having a blowing agent weight loss at least 15% to 50% lower compared to said expandable particles in the same predetermined time at room temperature so that said foamed cellular particles can be used in conventional equipment to form said foam articles with a bulk density ranging between about 0.50 pounds per cubic foot (8.0 kilograms per cubic meter) and 6.0 pounds per cubic foot (96.1 kilograms per cubic meter) without impregnation of said foamed cellular particles with an additional amount of blowing agent prior to ~~the pre-expansion/molding~~ further expansion/molding of said foamed cellular particles to form said foam articles.
2. (canceled)
3. (original) Foamed cellular particles of claim ~~[[2]]~~ 1 wherein said blowing agent is selected from the group consisting of acetone, methyl acetate, butane, hexane, n-pentane, cyclopentane, cyclohexane, isopentane, isobutane, neopentane, and mixtures thereof in an amount ranging between 2.5 wt % and 3.5 wt %.
4. (original) Foamed cellular particles of claim 3 wherein said blowing agent is n-pentane and mixtures thereof in an amount ranging between 2.5 wt % and 3.5 wt %.
5. (original) Foamed cellular particles of claim 1 wherein said particles contain an established cell structure comprising an average cell size ranging between 5 and 100 microns and a fixed number of cells.

6. (currently amended) Foamed cellular particles of claim 1 wherein said foamed cellular particles are comprised of a polymer composition comprised of: i) at least one C₈-C₁₂ vinyl aromatic monomer which is unsubstituted or substituted by one or more substituents selected from the group consisting of C₁₋₆ alkyl radicals and halogen atoms in an amount ranging from about 70 to about 100 weight %, ii) at least one monomer selected from the group consisting of C₃₋₆ ethylenically unsaturated carboxylic acids, anhydrides, imides and C₁₋₁₂ alkyl and alkoxyalkyl esters thereof, and C₃₋₆ ethylenically unsaturated nitriles in an amount ranging from about 30 to 0 weight % based on the weight of the polymer composition, and iii) [[a]] said organic blowing agent.

7. (currently amended) Foamed cellular particles of claim 6 wherein i) is selected from the group consisting of styrene, alpha methyl styrene, para methyl styrene, chlorostyrene and bromo-styrene, ii) is selected from the group consisting of methyl acrylate, ethyl acrylate, butyl acrylate, methyl methacrylate, ethyl methacrylate, acrylonitrile, methacrylonitrile, maleic anhydride[[d]], acrylic acid, methacrylic acid, itaconic acid, and maimide, and iii) is selected from the group consisting of acetone, methyl acetate, butane, hexane, n-pentane, cyclopentane, isopentane, isobutane, neopentane, HFC's, CFC's, HCFC's, water and mixtures thereof.

8. (original) Foamed cellular particles of claim 7 wherein i) is styrene, ii) is butyl acrylate, and iii) is n-pentane and mixtures thereof.

9. (currently amended) Foamed cellular particles of claim 1 wherein said foamed cellular particles are comprised of a polymer composition comprised of: i) at least one C₈-C₁₂ vinyl aromatic monomer which is unsubstituted or substituted by one or more substituents selected from the group consisting of C₁₋₆ alkyl radicals and halogen atoms in an amount ranging from about 70 to about 100 weight %, ii) at least one polymer selected from the group consisting of polyphenylene oxide, butadiene rubber, and high impact polystyrene in an amount ranging between about 30 and 0 weight % and iii) [[a]] said organic blowing agent.

10. (original) Foamed cellular particles of claim 9 wherein i) is selected from the group consisting of styrene, alpha methyl styrene, para methyl styrene,

chlorostyrene and bromo-styrene and iii) is selected from the group consisting of acetone, methyl acetate, butane, hexane, n-pentane, cyclopentane, isopentane, isobutane, neopentane, HFC's, CFC's, HCFC's, water, and mixtures thereof.

11. (original) Foamed cellular particles of claim 1 wherein said expandable polymer particles are formed in a polymerization process selected from the group consisting of suspension, bulk, and solution.

12. (original) Foamed cellular particles of claim 11 wherein said polymerization process is a suspension process.

13. (original) Foamed cellular particles of claim 12 wherein said suspension process is selected from the group consisting of one-step and two-step processes.

14. (original) Foamed cellular particles of claim 1 wherein said expandable polymer particles are formed in an extrusion process.

15. (original) Foamed cellular particles of claim 1 wherein said foamed cellular particles are formed in a heating process selected from the group consisting of contact heating, non-contact heating, infrared heating, microwave heating, dielectric heating, and radio frequency heating.

16. (original) Foamed cellular particles of claim 1 wherein said foamed cellular particles are formed in a heating process including a fluid bed dryer.

17. (original) Foamed cellular particles of claim 1 wherein said foamed cellular particles are formed in a heating process including a pre-expander.

18. (original) Foamed cellular particles of claim 1 wherein said expandable particles are produced from a polymer composition in a suspension polymerization process, the steps comprising:

admixing at least one styrenic monomer in an amount ranging from about 70 to about 100 weight % based on the amount of polymer composition with at least one vinyl group monomer in an amount ranging from about 30 to 0 weight % based on the polymer composition to form expandable particles, and

prior to, during, or after said suspension polymerization process mixing in said blowing agent selected from the group consisting of acetone, methyl acetate, butane, n-pentane, cyclopentane, cyclohexane, isopentane,

neopentane, isobutane, hexane, HFC's, CFC's, HCFC's, water, and mixtures thereof with said styrenic monomer and vinyl group monomer.

19. (original) Foamed cellular particles of claim 1 wherein said expandable particles are produced from a polymer composition in a suspension polymerization process, the steps comprising:

admixing at least one styrenic monomer in an amount ranging from about 70 to about 100 weight % based on the amount of polymer composition with at least one

polymer selected from the group consisting of polyphenylene oxide, butadiene rubber, and high impact polystyrene in an amount ranging between about 30 and 0 weight % based on the polymer composition to form expandable particles, and

prior to, during, or after said suspension polymerization process, mixing in said blowing agent selected from the group consisting of acetone, methyl acetate, butane, n-pentane, cyclopentane, cyclohexane, isopentane, neopentane, isobutane, hexane, HFC's, CFC's, HCFC's, water, and mixtures thereof with said styrenic monomer and said polymer.

20. (original) Foamed cellular particles of claim 1 wherein said expandable particles are produced from a polymer composition in an extrusion process, the steps comprising:

admixing a styrenic polymer in an amount ranging between about 70 and about 100 weight % based on the amount of polymer composition with at least one vinyl group polymer in an amount ranging between about 30 and 0 weight % based on the polymer composition,

heating and admixing said polymer composition to obtain a polymer melt and injecting said blowing agent selected from the group consisting of acetone, methyl acetate, butane, n-pentane, isobutane, cyclopentane, cyclohexane, isopentane, neopentane, hexane, HFC's, CFC's, HCFC's, water, and mixtures thereof,

extruding the polymer melt as a strand and chopping it into pellets, and

heating the pellets to a temperature range of about 70 and 110 °C at a pressure range of about 10.1 psi absolute (70 kPa) to about 24.7 psi absolute (170 kPa) thereby forming said foamed cellular particles.

21. (original) Foamed cellular particles of claim 1 wherein said expandable particles are produced from a polymer composition in an extrusion process, the steps comprising:

admixing a styrenic polymer in an amount ranging between about 70 and about 100 weight % based on the amount of polymer composition with at least one polymer selected from the group consisting of polyphenylene oxide, butadiene rubber, and high impact polystyrene in an amount ranging between about 30 and 0 weight % based on the polymer composition,

heating and admixing said polymer composition to obtain a polymer melt,

extruding the polymer melt as a strand and chopping said strand into pellets,

impregnating the pellets with said blowing agent selected from the group consisting of acetone, methyl acetate, butane, n-pentane, isobutane, cyclopentane, cyclohexane, isopentane, neopentane, hexane, HFC's, CFC's, HCFC's, water, and mixtures thereof, and

heating the pellets to a temperature range of about 70 and 110 °C at a pressure range of about 10.1 psi absolute (70 kPa) to about 24.7 psi absolute (170 kPa) thereby forming said foamed cellular particles.

22. (original) Foamed cellular particles of claim 1 wherein at least said foamed particles contain a coating composition.

23. (original) Foam particles of claim 22 wherein said coating composition is selected from the group consisting of silicones, metals, and glycerol carboxylates, and mixtures thereof.

24. (original) Foam particles of claim 23 wherein said glycerol carboxylates are selected from the group consisting of glycerol mono-stearate, glycerol di-stearate, glycerol tri-stearate, zinc stearate, calcium stearate, and magnesium stearate, and mixtures thereof.

25. (currently amended) A system for extending the shelf life of expandable polymer particles by ~~making~~using said foamed cellular particles of claim 1.

26. (previously presented) A foam article formed from the foamed cellular particles of claim 1.

27. (withdrawn-currently amended) A process for preparing foamed cellular particles comprised of a polymer composition for use in making foam articles, the steps comprising:

a) heating expandable polymer particles with a bulk density ranging between about 40 pounds per cubic foot (641 kilograms per cubic meter) and about 32.0 pounds per cubic foot (513 kilograms per cubic meter) and ~~[[a]]~~ organic blowing agent in an amount less than about 10.0 weight % based on the weight of the polymer composition at a temperature ranging between about 70 and 110°C and at a pressure ranging between about 10.1 psi absolute (70 kPa) and about 24.7 psi absolute (170 kPa) to form said foamed cellular particles with a bulk density ranging from between 34.3 pounds per cubic foot (550 kilograms per cubic meter) and about 12.5 pounds per cubic foot (200 kilograms per cubic meter) and ~~[[a]]~~ organic blowing agent in an amount ~~less than about 6.0~~ ranging between 2.50 and 5.0 weight % based on the weight of the polymer composition.

28. (withdrawn) A process of claim 27 wherein step a) is performed at a polymer producer's plant, and the steps further comprising:

b) at a foam molder's plant, subjecting said foamed cellular particles to conventional equipment to form foam articles with a bulk density ranging between about 0.80 pounds per cubic foot (12.8 kilograms per cubic meter) and 6.0 pounds per cubic foot (96.1 kilograms per cubic meter) without the need to impregnate said foamed cellular particles with an additional amount of blowing agent prior to expanding and molding.

29. (withdrawn-currently amended) A system for optimizing the shipping and packaging of polymer particles for use in making foam articles, the steps comprising:

at the polymer producer's plant,

a) using expandable polymer particles with a bulk density ranging between about 40 pounds per cubic foot (641 kilograms per cubic meter) and about 32.0 pounds per cubic foot (513 kilograms per cubic meter) and ~~[[a]]~~ organic blowing agent in an amount less than about 10.0 weight % based on the weight of the polymer composition and heating said expandable particles at a temperature ranging between about 70°C and about 110° C and at a

pressure ranging between about 10.1 psi absolute (70 kPa absolute) and about 24.7 psi absolute (170 kPa absolute) to form foamed cellular particles with a bulk density ranging from between about 34.3 pounds per cubic foot (550 kilograms per cubic meter) and about 12.5 pounds per cubic foot (200 kilograms per cubic meter) and with ~~[[a]]~~ organic blowing agent in an amount ~~less than 6.0~~ ranging between 2.50 and 5.0 weight % based on the weight of the polymer composition;

b) packaging said foamed cellular particles of step a) whereby the required strength of the packages used in transporting the foamed cellular particles of step a) is lower than the required strength of packages used when transporting the expandable particles with a higher bulk density and higher blowing agent level of step a); and

c) transporting said foamed cellular particles at a total shipment weight substantially equal to the total shipment weight of the expandable particles of step a) when transporting said expandable particles.

30. (withdrawn-currently amended) A system of claim 29 wherein in step a) said expandable particles are heated at a temperature ranging between 80°C and 110°C and at a pressure of about 13.8 psi absolute (95 kPa absolute) and about 16 psi absolute (110 kPa absolute) for about .05 to 60 minutes; wherein the bulk density of said foamed cellular particles ranges between about 28.1 pounds per cubic foot (450 kilograms per cubic meter) and about 21.9 pounds per cubic foot (350 kilograms per cubic meter); and wherein said blowing agent in the foamed cellular particles is in an amount ranging between about ~~[[2.0]]~~ 2.50 wt % and 5.0 wt %.

31. (withdrawn) A system of claim 29 wherein said blowing agent is selected from the group consisting of acetone, methyl acetate, butane, hexane, n-pentane, cyclopentane, cyclohexane, isobutane, isopentane, neopentane, HFC's, CFC's, HCFC's, water, and mixtures thereof in combination with carbon dioxide, nitrogen, and air.

32. (withdrawn) A system of claim 31 wherein said blowing agent is selected from the group consisting of acetone, methyl acetate, butane, hexane, n-pentane, cyclopentane, cyclohexane, isopentane, isobutane, neopentane, and

mixtures thereof in an amount ranging between 2.5 and 3.5 weight % based on the weight of the polymer composition.

33. (withdrawn) A system of claim 32 wherein said blowing agent is selected from the group consisting of pentane and mixtures thereof in an amount ranging between 2.5 and 3.5 weight % based on the weight of the polymer composition.

34. (withdrawn) A system of claim 29 wherein the packages used in transporting the cellular particles are selected from the group consisting of paper bags, plastic film bags, fiber cartons, metal drums, fiber drums, bulk bags, and returnable packaging.

35. (withdrawn) A system of claim 29 wherein the total weight of the foamed cellular particles of step c) transported by said transportation means is about 30,000 to about 50,000 pounds.

36. (withdrawn) A system of claim 29 wherein said expandable polymer particles are formed in a polymerization process selected from the group consisting of suspension, bulk, and solution.

37. (withdrawn) A system of claim 36 wherein said polymerization process is a suspension process.

38. (withdrawn) A system of claim 37 wherein said suspension polymerization process is selected from the group consisting of one-step and two-step processes.

39. (withdrawn) A system of claim 29 wherein said expandable polymer particles are formed in an extrusion process.

40. (withdrawn) A system of claim 29 wherein said foamed cellular particles are transported to a foam molder's plant and the steps further comprising:
d) in said foam molder's plant, subjecting said foamed cellular particles to conventional equipment to form a foam article with a bulk density ranging between about 0.80 pounds per cubic foot (12.8 kilograms per cubic meter) and 6.0 pounds per cubic foot (96.1 kilograms per cubic meter) without the need to impregnate said foamed cellular particles with an additional amount of blowing agent prior to expanding and molding.

41. (withdrawn) A system of claim 29 wherein said foamed cellular particles are formed in a heating process selected from the group consisting of contact

heating, non-contact heating, infrared heating, microwave heating, dielectric heating, and radio frequency heating in said plant of said polymer producer.

42. (withdrawn) A system of claim 31 wherein said foamed cellular particles are formed in a heating process including a fluid bed dryer.

43. (withdrawn) A system of claim 29 wherein each said foamed cellular particle has an established cell structure comprising an average cell size ranging between 5 and 100 microns and a fixed number of cells.

44. (withdrawn) A system of claim 29 wherein said expandable particles are produced from a polymer composition in a suspension polymerization process, the steps comprising:

admixing at least one styrenic monomer in an amount ranging from about 70 to about 100 weight % based on the amount of polymer composition with at least one vinyl group monomer in an amount ranging from about 30 to 0 weight % based on the polymer composition to form expandable particles, and

prior to, during, or after said suspension polymerization process mixing in said blowing agent selected from the group consisting of acetone, methyl acetate, butane, n-pentane, cyclopentane, cyclohexane, isopentane, neopentane, isobutane, hexane, HFC's, CFC's, HCFC's, water, and mixtures thereof with said styrenic monomer and vinyl group monomer.

45. (withdrawn) A system of claim 29 wherein said expandable particles are produced from a polymer composition in a suspension polymerization process, the steps comprising:

admixing at least one styrenic monomer in an amount ranging from about 70 to about 100 weight % based on the amount of polymer composition with at least one

polymer selected from the group consisting of polyphenylene oxide, butadiene rubber, and high polystyrene in an amount ranging between about 30 and 0 weight % based on the polymer composition to form expandable particles, and

prior to, during, or after said suspension polymerization process, mixing in said blowing agent selected from the group consisting of acetone, methyl acetate, butane, n-pentane, cyclopentane, cyclohexane, isopentane,

neopentane, isobutane, hexane, HFC's, CFC's, HCFC's, water, and mixtures thereof with said styrenic monomer and said polymer.

46. (withdrawn) A system of claim 29 wherein said expandable particles are produced from a polymer composition in an extrusion process, the steps comprising:

admixing a styrenic polymer in an amount ranging between about 70 and about 100 weight % based on the amount of polymer composition with at least one vinyl group polymer in an amount ranging between about 30 and 0 weight % based on the polymer composition,

heating and admixing said polymer composition to obtain a polymer melt and injecting said blowing agent selected from the group consisting of acetone, methyl acetate, butane, n-pentane, isobutane, cyclopentane, cyclohexane, isopentane, neopentane, hexane, HFC's, CFC's, HCFC's, water, and mixtures thereof,

extruding the polymer melt as a strand and chopping it into pellets, and

heating the pellets to said temperature range of about 70 and 110 °C at said pressure range of about 10.1 psi absolute to about 24.7 psi absolute thereby forming said foamed cellular particles.

47. (withdrawn) A system of claim 29 wherein said expandable particles are produced from a polymer composition in an extrusion process, the steps comprising:

admixing a styrenic polymer in an amount ranging between about 70 and about 100 weight % based on the amount of polymer composition with at least one polymer selected from the group consisting of polyphenylene oxide, butadiene rubber, and high impact polystyrene in an amount ranging between about 30 and 0 weight % based on the polymer composition,

heating and admixing said polymer composition to obtain a polymer melt,

extruding the polymer melt as a strand and chopping said strand into pellets,

impregnating the pellets with said blowing agent selected from the group consisting of acetone, methyl acetate, butane, n-pentane, isobutane,

cyclopentane, cyclohexane, isopentane, neopentane, hexane, HFC's, CFC's, HCFC's, water, and mixtures thereof, and

heating the pellets to said temperature range of about 70 and 110 °C at said pressure range of about 10.1 psi absolute to about 24.7 psi absolute thereby forming said foamed cellular particles.

48. (withdrawn) A system of claim 29 the steps further comprising:

prior to, during, or after step a) applying a coating composition to said expandable polymer particles or to said foamed cellular particles.

49. (original) Foamed cellular particles of claim 1 wherein said expandable particles are produced from a polymer composition formed in a polymerization process in an extruder, the steps comprising:

admixing a styrenic monomer in an amount ranging between about 70 and 100 weight % based on the amount of monomer composition with at least one vinyl group monomer in an amount ranging between about 30 and 0 weight % based on the monomer composition to form said polymer composition,

heating said polymer composition to obtain a polymer melt and injecting said blowing agent selected from the group consisting of acetone, methyl acetate, butane, n-pentane, isobutane, cyclopentane, cyclohexane, isopentane, neopentane, hexane, HFC's, CFC's, HCFC's, water, and mixtures thereof,

extruding the polymer melt as a strand and chopping it into pellets, and

heating the pellets to a temperature range of about 70 and 110 °C at a pressure range of about 10.1 psi absolute (70kPA) to about 24.7 psi absolute (170 kPA) thereby forming said foamed cellular particles.

50. (withdrawn) A system of claim 29 wherein said expandable particles are produced from a polymer composition formed in a polymerization process in an extruder, the steps comprising:

admixing a styrenic monomer in an amount ranging between about 70 and 100 weight % based on the amount of monomer composition with at least one vinyl group monomer in an amount ranging between about 30 and 0 weight % based on the monomer composition to form said polymer composition,

heating said polymer composition to obtain a polymer melt and injecting said blowing agent selected from the group consisting of acetone, methyl acetate, butane, n-pentane, isobutane, cyclopentane, cyclohexane, isopentane, neopentane, hexane, HFC's, CFC's, HCFC's, water, and mixtures thereof,

extruding the polymer melt as a strand and chopping it into pellets, and

heating the pellets to a temperature range of about 70 and 110 °C at a pressure range of about 10.1 psi absolute (70kPA) to about 24.7 psi absolute (170 kPA) thereby forming said foamed cellular particles.